

Artikel	Samenstelling %				Smelttraject		Standaard	
	Sn	Pb	Ag	Cu	Solidus °C	Liquidus °C	ISO 9453	EN 29453
SnCu3	97	12	-	3	227	310	402	S-Sn97Cu3
SnAg3	96,5	-	3	-	221	221	703	S-Sn97Ag3
SnPb20	80	20	-	-	183	205	-	-
SnPb37	63	37	-	-	183	183	101	S-Sn63Pb37
SnPb40	60	40	-	-	183	190	103	S-Sn60Pb40
SnPb50	50	50	-	-	183	215	111	S-Pb50Sn50
SnPb60	40	60	-	-	183	235	114	S-Pb60Sn40
Pb100	-	100	-	-	327	327	-	-