

Artikel	Samenstelling %					Smelttraject		Dichtheid	Treksterkte	Standaard		
	Ag	Cu	Zn	Sn	Si	Solidus °C	Liquidus °C			ISO 17672	EN 1044	AWS A5.8
Zonder Sn												
Ag20	20	44	36	-	0,15	610	810	8,7	43	-	AG 206	-
Ag30	30	38	32	-	-	680	765	8,9	50	Ag 230	AG 204	BAG-20
Ag44	44	30	26	-	-	675	735	9,1	51	Ag 244	AG 203	-
Met tin												
Ag30Sn	30	36	32	2	-	665	755	8,8	48	Ag 130	AG 107	-
Ag34Sn	34	36	27,5	2,5	-	630	730	9	48	Ag 134	AG 106	-
Ag40Sn	40	30	28	2	-	650	710	9,1	44	Ag 140	AG 105	BAG-28
Ag45Sn	45	27	25,5	2,5	-	640	680	9,2	43	Ag 145	AG 104	BAG-36
Ag55Sn	55	21	22	2	-	630	660	9,4	44	Ag 155	AG 103	-
Ag56Sn	56	22	17	5	-	620	655	9,4	48	Ag 156	AG 102	BAG-7